

**3.AATCC TM8:2016e – Colorfastness to Crocking: AATCC Crockmeter Method**

**Staining Evaluation Method:** Gray Scale for Staining

**Test Results:**

Specimen/Sample	Original	
	Dry	Wet
Style: 1342-04 Carrick	4.5	4.5

**Rating System:**

- Grade 5, Negligible Color Staining
- Grade 4, Slight Color Staining
- Grade 3, Noticeable Color Staining
- Grade 2, Considerable Staining
- Grade 1, Excessive Color Staining

**4.16 CFR 1640: Standard for the Flammability of Upholstered Furniture, CA TB 117: 2013 - Smolder Resistance of Materials Used in Upholstered Furniture**

Section 1 – Cover Fabric Test

Style: 1342-05 Carrick

	Initial Test		
	Vertical Char Length (in)	Mock-up Specimen Continues to Smolder after 45 minutes	Mock-up Specimen Transitions to Open Flaming
Specimen 1	1.1	No	No
Specimen 2	0.9	No	No
Specimen 3	0.9	No	No

**Conclusion:**

The Sample submitted for testing **Passes** the requirements in 16 CFR PART 1640.5 Standard For The Flammability of Upholstered Furniture, California Technical Bulletin 117-2013 Section 1: Cover Fabric Test

**For and on behalf of  
Intertek Products Group North America:**

Edwin Serrano  
Edwin Serrano  
Feb 23 2022 11:28 AM

**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156

