

TEST REPORT

Applicant: Brentano Inc
260 Holbrook Drive
Wheeling, IL 60090

Attention: Lan Chenh

E-Mail: lchenh@brentanofabrics.com

Sample Description as Declared:

Sample Description : Fabric – Upholstery
Color : 6527-01
Style # : 6527
Order # /PO # : DES2356
Fabric/Garment Weight : Not Provided
Fiber Content : 93% Polyester, 5% PI Recycled, 2% PC Recycled Polyester
No. of Samples: 1
End Use : Upholstery
Finishing : Stain Resistant and Acrylic Backing
Care Instructions : Not Provided
Previous Report # : Not Applicable
Sample Received Date : June 07, 2018
Final Confirmation Received Date: June 07, 2018
Report Completion Date : June 14, 2018



For and on behalf of
Intertek Products Group North America :



Edwin Serrano
Account Manager

Intertek North America

545 E Algonquin Road, Suite F
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY
AT-1348

TEST RESULTS:

Style# : 6527

BREAKING STRENGTH

ASTM D 5034

Average in (lbf)

Warp	215.2
Weft	423.9

YARN SLIPPAGE

ASTM D 4034

	SEAM OPENED AT ¼"/6MM	SEAM STRENGTH Average (lbf)	TYPE OF SEAM RUPTURE
Warp	*	69.1	STB
Weft	*	84.1	STB

REMARK: STB = SEWING THREAD BREAK

* =THE SEAM OPENING WAS LESS THAN ¼INCH/6MM THOUGH THE ULTIMATE SEAM STRENGTH WAS FOUND AS STATED

RESISTANCE TO PILLING AS RECEIVED: BRUSH PILLING TESTER

ASTM D 3511

Running Time: 4 Minutes, Then 2 Minutes

Average:	4.5
Fuzziness	Negligible

RATING SYSTEM

- Grade 5, No Pilling
- Grade 4, Slight Pilling
- Grade 3, Moderate Pilling
- Grade 2, Severe Pilling
- Grade 1, Very Severe Pilling

Intertek North America

545 E Algonquin Road, Suite F
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

Style# : 6527

CA TB 117:2013 – Smolder Resistance of Materials used in Upholstered Furniture

-Section 1: Cover Fabric Test

The cover fabric material submitted **Does Meet** the flame resistance requirements when tested in accordance with the Bureau of Electronic & Appliance Repair Home Furnishings and Thermal Insulation, Technical Bulletin 117 – 2013, Section 1: Cover fabric test

	Vertical Char length (Inches)	Mock-up specimen continues to smolder After 45 Minutes	Mock-up test specimen transitions to open flaming
Specimen 1	0.9	No	No
Specimen 2	0.9	No	No
Specimen 3	1.0	No	No


Requirements: A cover fabric material considered pass or fail based on following criteria

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a). The mock-up test specimen continues to smolder after 45 minutes test duration.
 - b). A vertical Char length (measured as specified in step 11.9 of ASTM E1353-08a^{ε1}) of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c). The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

Note: For Cover fabrics that pass this section, the first layer of filling materials located below the cover fabric shall also meet the test requirements of section 3 of CA TB -117 :2013

Intertek North America

545 E Algonquin Road, Suite F
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

Style# : 6527

NFPA 260-2013 - Standard Methods of Test and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture

The material submitted is an NFPA 260 Class I cover fabric when tested in accordance with NFPA 260, Fabric Classification Test Method.

Specimen #	Vertical Char Length (mm)
1	15
2	20
3	18

Classification:

Class 1 - This class includes all fabrics which exhibit a vertical char of less than 45 mm on each of the three replications when subjected to the fabric classification test of NFPA 260, Section 6.1.

The test results stated in this report relate only to the item(s) tested. This test report may not be reproduced except in full, without written approval of Intertek.

.....

*If you need assistance in interpreting these results or if you have any questions,
Please feel free to call Customer Service Department*

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Intertek North America

545 E Algonquin Road, Suite F
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156

