


TEST REPORT

Client: Brentano, Inc.
260 Holbrook Drive
Wheeling, IL 60090
Attention: Lan Chenh
E-Mail: lchenh@brentanofabrics.com

Sample Description as Declared :

Sample Description : Upholstery Fabric
Color : 4375 – 01 and 4375 – 08
Style # : Beallara 4375 / Laelia 4373
Fabric/Garment Weight : Not Provided
Fiber Content : 100% Polyester
No. of Samples: 2
End Use : CO Water Repellant
Care Instructions : See Product
Sample Received Date : March 02, 2023
Final Confirmation Received Date: March 03, 2023
Report Completion Date : March 07, 2023



For and on behalf of Intertek :

Edwin Serrano
Edwin Serrano Mar 8 2023 9:15 AM
DocSign

Intertek
545 E Algonquin Road, Suite H
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



Test Performed As Requested by Client:

16 CFR 1640: Standard for the Flammability of Upholstered Furniture, CA TB 117: 2013 - Smolder Resistance of Materials Used in Upholstered Furniture
Section 1 – Cover Fabric Test

Sample Description: Upholstery Fabric – Color: 4375 – 01

| Initial Test | | | |
|--------------|---------------------------|--|--|
| | Vertical Char Length (in) | Mock-up Specimen Continues to Smolder after 45 minutes | Mock-up Specimen Transitions to Open Flaming |
| Specimen 1 | 0.6 | No | No |
| Specimen 2 | 0.6 | No | No |
| Specimen 3 | 0.6 | No | No |

Conclusion:

The Sample submitted for testing **Passes** the requirements in 16 CFR PART 1640.5 Standard For The Flammability of Upholstered Furniture, California Technical Bulletin 117-2013
Section 1: Cover Fabric Test

ASTM D5034-2021 - Breaking Strength and Elongation of Textile Fabrics

Grab Test

Size of Clamps: 1" x 1" (Front); 1" x 3" (Back)

Sample Condition:

| SPECIMEN | | SAMPLE |
|----------|---------|--------------------------------------|
| | | Upholstery Fabric – Color: 4375 – 01 |
| | | BREAKING FORCE lbf |
| WARP | AVERAGE | 431.3 |
| WEFT | AVERAGE | 379.6 |