

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 29, 2021

Mr. Lan Chenh
BRENTANO
260 Holbrook Drive
Wheeling, IL 60090

Reference: Laboratory Test Report
Lab Identification No. 45467
Invoice No. 76761

Dear Mr. Chenh:

One (1) fabric sample, identified as **Pattern: Oracle 4290; Pattern Color: 4290-03; Fiber Contents: 100% FR Polyester**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” **Testing was performed using a non-flame retardant polyurethane foam with a density of 22 kg/m³.**

The sample submitted was tested to Section 3.1 Smouldering Cigarette Test. The results are as follows:

Test Results

Ignition Source

Smouldering Cigarette	#1	PASS (No flaming or progressive smouldering)
	#2	PASS (No flaming or progressive smouldering)

The sample submitted **meets** minimum requirements of the above standard when tested to the smouldering cigarette ignition source.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 29, 2021

Mr. Lan Chenh
BRENTANO
260 Holbrook Drive
Wheeling, IL 60090

Reference: Laboratory Test Report
Lab Identification No. 45467
Invoice No. 76761

Dear Mr. Chenh:

One (1) fabric sample, identified as **Pattern: Oracle 4290; Pattern Color: 4290-03; Fiber Contents: 100% FR Polyester**, was received and tested in accordance with **IMO 2010 FTP CODE - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture**, “The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazards of the product in use.” **Testing was performed using a non-flame retardant polyurethane foam with a density of 22 kg/m³.**

The sample submitted was tested to Section 3.2 Propane Flame Test. The results are as follows:

Test Results

Ignition Source

Propane Flame	#1	PASS (No flaming or progressive smouldering)
	#2	PASS (No flaming or progressive smouldering)

The sample submitted **meets** minimum requirements of the above standard when tested to the propane ignition source.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

