

**TEST RESULTS:**

Style# : Quickstep 4322

**RESISTANCE TO PILLING AS RECEIVED: BRUSH PILLING TESTER**

ASTM D 3511

Running Time: 4 Minutes, Then 2 Minutes

Average: 1.0

Hairiness /  
Fuzziness Moderate

**RATING SYSTEM**

Grade 5, No Pilling  
Grade 4, Slight Pilling  
Grade 3, Moderate Pilling  
Grade 2, Severe Pilling  
Grade 1, Very Severe Pilling

**NFPA 260-2013 - STANDARD METHODS OF TEST AND CLASSIFICATION SYSTEM FOR CIGARETTE  
IGNITION RESISTANCE OF COMPONENTS OF UPHOLSTERED FURNITURE**

The material submitted is an NFPA 260 Class I cover fabric when tested in accordance with NFPA 260, Fabric Classification Test Method.

Specimen #	Vertical Char Length (mm)
1	12
2	17
3	15

**Classification:**

Class 1 - This class includes all fabrics which exhibit a vertical char of less than 45 mm on each of the three replications when subjected to the fabric classification test of NFPA 260, Section 6.1.

**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348