

16 CFR 1640: Standard for the Flammability of Upholstered Furniture, CA TB 117: 2013 - Smolder Resistance of Materials Used in Upholstered Furniture

Section 1 – Cover Fabric Test

Sample Description: Upholstery Fabric, 6571 Renata / 6574 Anastasia

Initial Test			
	Vertical Char Length (in)	Mock-up Specimen Continues to Smolder after 45 minutes	Mock-up Specimen Transitions to Open Flaming
Specimen 1	0.7	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No
Specimen 2	0.7	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No
Specimen 3	0.6	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No

Conclusion:

The Sample submitted for testing Passes the requirements in 16 CFR PART 1640.5 Standard For The Flammability of Upholstered Furniture, California Technical Bulletin 117-2013

Color Fastness to Crocking: AATCC Crockmeter Method(AATCC TM8:2016e)

	Fabric Style: 6571 / 6574
Dry	4.5
Wet	4.5

Rating System:

- Grade 5, Negligible Color Staining
- Grade 4, Slight Color Staining
- Grade 3, Noticeable Color Staining
- Grade 2, Considerable Staining
- Grade 1, Excessive Color Staining

**For and on behalf of
Intertek Products Group North America:**

Edwin Serrano
Edwin Serrano
Feb 23 2022 11:28 AM

Intertek North America
545 E Algonquin Road, Suite F
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156

