


**TEST REPORT**

**Client:** Brentano, Inc.  
260 Holbrook Drive  
Wheeling, IL 60090  
**Attention:** Lan Chenh  
**E-Mail:** lchenh@brentanofabrics.com

**Sample Description as Declared :**

Sample Description : Upholstery Fabric  
Color : 9649-01 and 9649-04  
Style # : 9649  
Fabric/Garment Weight : Not Provided  
Fiber Content : 50% Acrylic, 25% Wool, 25% Polyester  
No. of Samples : 2  
Finish : Stain Resistant  
End Use : Upholstery  
Care Instructions : Not Provided  
Sample Received Date : February 28, 2020  
Final Confirmation Received Date : February 28, 2020  
Report Completion Date : March 5, 2020



**For and on behalf of  
Intertek Products Group North America:**

**Rita Pun**  
Digitally signed by  
Rita Pun  
Date: 2020.03.05  
18:51:28 -06'00'

**Intertek North America**  
545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



**CA TB 117:2013 – Smolder Resistance of Materials used in Upholstered Furniture**

*-Section 1: Cover Fabric Test*

The cover fabric material submitted **passes** the flame resistance requirements when tested in accordance with the Bureau of Electronic & Appliance Repair Home Furnishings and Thermal Insulation, Technical Bulletin 117 – 2013, Section 1: Cover fabric test

Component Description: Sample Descripton: Upholstery Fabric Color: 9649-01 Style No.: 9649			
Initial Test			
	Vertical Char length (Inches)	Mock-up specimen continues to smolder After 45 Minutes	Mock-up test specimen transitions to open flaming
Specimen 1	0.5	No	No
Specimen 2	0.6	No	No
Specimen 3	0.6	No	No

**Requirements: A cover fabric material considered pass or fail based on following criteria**

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
  - a). The mock-up test specimen continues to smolder after 45 minutes test duration.
  - b). A vertical Char length (measured as specified in step 11.9 of ASTM E1353-08a<sup>e1</sup>) of more than 1.8 inches (45 mm) develops on the cover fabric.
  - c). The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

**Note:** For Cover fabrics that pass this section, the first layer of filling materials located below the cover fabric shall also meet the test requirements of section 3 of CA TB -117 :2013