


TEST REPORT

Client: Brentano, Inc.
260 Holbrook Drive
Wheeling, IL 60090
Attention: Lan Chenh
E-Mail: Lchenh@brentanofabrics.com

Sample Description as Declared :

Sample Description : Upholstery Fabric
Color : Testing Sample
Style # : 6597
Fabric/Garment Weight : Not Provided
Fiber Content : 39% Polyester, 32% Rayon, 29% Cotton
No. of Samples: 1
End Use : Upholstery
Care Instructions : See Product
Sample Received Date : January 05, 2023
Final Confirmation Received Date: January 05, 2023
Report Completion Date : January 11, 2023



Test Performed As Requested by Client:

16 CFR 1640: Standard for the Flammability of Upholstered Furniture, CA TB 117: 2013 - Smolder Resistance of Materials Used in Upholstered Furniture
Section 1 – Cover Fabric Test

Sample Description: Upholstery - (6597- Fabric)

Initial Test			
	Vertical Char Length (in)	Mock-up Specimen Continues to Smolder after 45 minutes	Mock-up Specimen Transitions to Open Flaming
Specimen 1	0.8	No	No
Specimen 2	0.9	No	No
Specimen 3	1.1	No	No

Conclusion:

The Sample submitted for testing **Passes** the requirements in 16 CFR PART 1640.5 Standard For The Flammability of Upholstered Furniture, California Technical Bulletin 117-2013
Section 1: Cover Fabric Test

ASTM D5034-2021 - Breaking Strength and Elongation of Textile Fabrics

Grab Test

Size of Clamps: 1" x 1" (Front); 1" x 3" (Back)

Sample Condition: Conditioned

SPECIMEN		SAMPLE
		Upholstery - (6597- Fabric)
		BREAKING FORCE lbf
WARP	AVERAGE	192.0
WEFT	AVERAGE	365.0